

MATERIAL AISI-1045		CENTRADO	TALADRADO	DESBASTE	SEMI-ACAB	ACABADO	RANURADO	ROSCADO
VELOCIDAD	Vc							
DE CORTE	m/min	20	25	120	150	200	100	120
AVANCE	F1	0.05	0.02	0.25	0.25	0.3	0.07	
	F2			0.2		0.2	0.07	
	F3			0.25		0.07		
	F4					0.04		
MATERIAL AISI-4140		CENTRADO	TALADRADO	DESBASTE	SEMI-ACAB	ACABADO	RANURADO	ROSCADO
VELOCIDAD	Vc							
DE CORTE	m/min	20	25	120	150	200	100	100
AVANCE	F1	0.05	0.02	0.25	0.25	0.3	0.07	
	F2			0.2		0.2	0.07	
	F3			0.25		0.07		
	F4					0.04		
MATERIAL FUNDICION GRIS		CENTRADO	TALADRADO	DESBASTE	SEMI-ACAB	ACABADO	RANURADO	ROSCADO
VELOCIDAD	Vc							
DE CORTE	m/min	25	25	100	130	180	80	100
AVANCE	F1	0.1	0.2	0.3	0.25	0.3	0.1	
	F2			0.25		0.2	0.1	
	F3			0.3		0.07		
	F4					0.04		
MATERIAL ALUMINIO		CENTRADO	TALADRADO	DESBASTE	SEMI-ACAB	ACABADO	RANURADO	ROSCADO
VELOCIDAD	Vc							
DE CORTE	m/min	80	80	300	300	300	150	150
AVANCE	F1	0.1	0.2	0.3	0.25	0.3	0.1	
	F2			0.25		0.2	0.1	
	F3			0.3		0.07		
	F4					0.04		
MATERIAL ACERO INOX.		CENTRADO	TALADRADO	DESBASTE	SEMI-ACAB	ACABADO	RANURADO	ROSCADO
VELOCIDAD	Vc							
DE CORTE	m/min	10	15	80	80	10	50	80
AVANCE	F1	0.05	0.1	0.25	0.25	0.3	0.07	
	F2			0.2		0.2	0.07	
	F3			0.25		0.07		
	F4					0.04		
	L.D.							